

Hebei Guangsou Technology Co., LTD

ADD:300 meters west of Nanzhai Village, Chengyouzi Township, Anping County, Hengshui City, Hebei Province (north of Xiaogong Road)

Tel:8615503256665 Fax:8603187663666 Postcode):053600

Website:WWW.fiberglassmeshltd.com

E-mail:amy@bestingltd.com

TECHNICAL DATA SHEET

ITEM: GST MESH 75 GSM

HS CODE:7019902100

Specifications: ARNP5*5-100T 75GSM

Number	Test item		Unit	Standard	Result
1	Original Tensile breakingforce	Warp	N/5cm	≥ 750	850
		Weft	N/5cm	≥ 750	850
2	Hole	Warp	mm	5 ± 0.5	5
		Weft	mm	5 ± 0.5	5
3	Width		cm	100 ± 1	100
4	Mass per unit area		g/m^2	≥ 75	75
5	Latex content		g/m^2	≥ 15	16
6	Breaking elongation		%	≤ 5.0	3.5
7	Appearance		UPON REQUIREMENT		White
8	AR remained strength		AR Remained strength based on JG158-2004 standard		89%

All statements herein are expressions of opinion, which we believe to be accurate and reliable, but are presented without guarantee or responsibility on our part. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or

implied, is made or intended. Values presented above are nominal and only to be used as guidelines.

GUANGSOU